

Determination of Physical and Mechanical Properties of Wood Specie *Dinizia excelsa* Ducke

Natália Garcia Couto¹, Vinicius Borges de Moura Aquino¹, João Paulo Boff Almeida¹,
Diego Henrique de Almeida², André Luis Christoforo^{1,*}, Francisco Antonio Rocco Lahr³

¹Department of Civil Engineering (DECiv), Federal University of São Carlos (UFSCar), São Carlos, Brazil

²Department of Civil Engineering, Federal University of Rondônia Foundation (UNIR), Rondônia, Brazil

³Department of Structural Engineering (SET), São Carlos Engineering School, São Paulo University (EESC/USP), São Carlos, Brazil

Abstract Wood is a material, when compared with other materials applied in civil construction, displays several advantages such as an elevated mechanical strength when related with its apparent density. The wood manufacturing industry has great representativeness in the Brazilian economy however, the irrational consumption of determined species brought damages to the forest, causing extinction of some species and consequently, rising wood prices in market. The characterization of unknown wood species presents an alternative for a more rational exploration and expand wood use in structural purpose, enabling the use of this species determining its properties. The study aimed to characterize 3 physical properties and 12 mechanical properties of *Angelim vermelho* (*Dinizia excelsa* Ducke.) based on Brazilian Standard ABNT NBR 7190. Twelve models were used for each test, totaling 180 experimental results. The analysis of variance (ANOVA) handling the regression models will be used to predict the strength and stiffness as function of apparent density. The results presented on tests demonstrated compatible performance with common wood species used in civil construction, considered high strength wood and with adequate use in this activity. According to the regression models, only three properties were considered significant with apparent density estimation.

Keywords Characterization, *Dinizia excelsa* Ducke, Regression model, Analysis of variance (ANOVA)

1. Introduction

Wood is a functional material due to its anatomical characteristics, physical and mechanical properties. Also is a renewable material compared to others used in civil construction, like concrete, steel and aluminum, presents advantages as elevated mechanical strength in relation to mass, low energetic consumption in its processing and good thermal isolation [1].

Brazil is highlighted in world scene when it refers to the wood manufacturing industry due to the diversity of native forests and the planted forest productivity. The high native forest wood consumption for a long time led to a nearly extinction of many economic value wood species [2]. Wood harvest, mainly Amazonian native wood species, has been done in a uncontrolled form bringing enormous losses to the forests and ignoring high potential unknown wood species [3].

Among the sectors that use wood as raw material, civil construction sector is the one of the most exigent in terms of physical and mechanical properties. Then, it causes a certain limitation in the number of wood species with characteristics that could be used in this sector [4, 5].

The knowledge of physical and mechanical properties results in a better utilization of wood species that is constantly rejected due to lack of information. It is important a transformation in this scenario for the wood structures become more competitive when compared to other types of materials [6].

According Dias and Lahr [7], the methods of unknown wood species tests established on the Brazilian Standard ABNT NBR 7190 [8] demands the use of large and expensive equipment available in research centers. Therefore, many times wood is used without knowledge of its characteristics, which leads to its waste.

Otherwise, a physical property of easy determination experimentally is the apparent density, defined by the ratio between the mass and volume of the sample at 12% moisture. Considering that density is a basic physical property, its value endorses the estimation of some wood properties [9, 10]. The estimation of strength and stiffness properties by density via mathematical methods (regression methods) enables the engineer a better pre-design of the structure.

* Corresponding author:

alchristoforo@gmail.com (André Luis Christoforo)

Published online at <http://journal.sapub.org/ijme>

Copyright © 2018 The Author(s). Published by Scientific & Academic Publishing

This work is licensed under the Creative Commons Attribution International

License (CC BY). <http://creativecommons.org/licenses/by/4.0/>

The wood *Dinizia excelsa* Ducke., displayed in Figure 1, present in Brazilian states of Acre, Rondônia, Amazonas, Pará, Roraima, Amapá e Maranhão becomes a great option, especially to Amazonian part of Brazil, the west and southeast part of Brazilian country, where the production of this wood specie is more noticeable [11].



Figure 1. Image of the *Dinizia excelsa* Ducke, Source: http://www.ipt.br/informacoes_madeiras/23.html

Observing the exposed, the study aims to characterize the *Dinizia excelsa* wood specie and evaluate the possibility of estimating physical and mechanical properties in function of apparent density.

2. Material and Methods

The wood samples of the *Dinizia excelsa* Ducke has been properly stored, close to 12% moisture content, the moisture balance established by the Brazilian standard [8].

All tests were carried out on the Laboratory of Wood and Wood Structures (*Laboratório de Madeira e de Estruturas de Madeira - LaMEM*), at the São Carlos Engineering School (EESC), University of São Paulo (USP).

The physical and mechanical properties (Table 1) were obtained according to the assumptions and calculation methods given by the Brazilian standard ABNT NBR 7190 [7] (Wooden Structures Project), provided on its Annex B. It should be noted that 12 values for each one of its physical (3) and mechanical properties (12) were investigated, resulting in a total of 180 experimental values obtained.

In addition to obtaining the physical and mechanical properties listed in Table 1, the wood *Dinizia excelsa* Ducke has been properly classified in the timber strength classes [8], defined by determining its characteristic value of compressive strength parallel to the grain ($f_{c0,k}$).

To estimate the strength and the stiffness properties (Y), as a function of the apparent density (ρ_{12}) of the *Dinizia excelsa* Ducke wood specie, regression models were used (Equations 1 to 4) based on analysis of variance (ANOVA), tested in a way to establish the best fit for estimated property.

$$Y = a + b \cdot \rho_{12} \quad [\text{Lin - linear}] \quad (1)$$

$$Y = a \cdot e^{b \cdot \rho_{12}} \quad [\text{Exp - exponential}] \quad (2)$$

$$Y = a + b \cdot \ln(\rho_{12}) \quad [\text{Log - logarithmic}] \quad (3)$$

$$Y = a \cdot \rho_{12}^b \quad [\text{Geo - geometric}] \quad (4)$$

By ANOVA regression models, considering the 5% level of significance (α), the formulated null hypothesis consisted by the non-representativeness of the tested models ($H_0: \beta = 0$), and the representativeness as an alternative hypothesis ($H_1: \beta \neq 0$). P-value greater than the significance level implies in the accepting H_0 (the model tested is not representative - ρ_{12} variations are unable to explain the variation in strength and stiffness property), refuting it otherwise (the model tested is representative).

Besides the use of ANOVA, which allows to accept or not the representativeness of the tested models, the coefficient of determination values (R^2) were obtained as a way to evaluate the variation capability in the apparent density to explain the estimated dependent variable, making it possible to determine, among the considered significant models (4 models for each of the 14 strength properties and estimated stiffness – resulting in 48 adjustments), the ones with the best fit.

Table 1. Mechanical and physical properties measured for the *Dinizia excelsa* Ducke wood specie

Properties	Notation
Apparent density	ρ_{12}
Total radial Shrinkage	RTT
Total tangencial Shrinkage	RTT
Compressive strength parallel to the grain	f_{c0}
Tensile strength parallel to the grain	f_{t0}
Tensile strength normal to the grain	f_{t90}
Shear strength parallel to the grain	f_{v0}
Splitting strength	f_{s0}
Conventional strength on static bending test	f_m
Modulus of elasticity in parallel directions to the grain	E_{c0}
Modulus of elasticity in tension parallel to the grain	E_{t0}
Conventional modulus of elasticity on static bending test	E_m
Hardness parallel to the grain	f_{H0}
Hardness normal to the grain	f_{H90}
Toughness	W

3. Results and Discussion

Tables 2 and 3 shows the mean values (\bar{x}), coefficient of variation (Cv), the lowest (Min) and the highest (Max) of the physical and mechanical properties of the *Dinizia excelsa* Ducke wood, respectively.

Table 2. Physical properties results for the *Dinizia excelsa* Ducke wood

Stat.	ρ_{12} (kg/m ³)	RTT (%)	RTT (%)
\bar{x}	1130	5.10	8.42
Cv	0.10	0.12	0.08
Min	990	4.40	7.44
Max	1250	6.54	9.68

Table 3. Mechanical properties results for the *Dinizia excelsa* Ducke wood

Stat.	f_{c0} (MPa)	f_{t0} (MPa)	f_{h90} (MPa)	f_{v0} (MPa)
\bar{x}	78	105	4.8	19
Cv	0.08	0.33	0.28	0.23
Min	66	59	2.8	12
Max	90	198	8.1	26
Stat.	f_{s0} (MPa)	f_m (MPa)	E_{c0} (MPa)	E_{t0} (MPa)
\bar{x}	0.9	110	16695	17024
Cv	0.12	0.14	0.18	0.17
Min	0.7	87	9494	12842
Max	1.0	129	20935	22730
Stat.	E_m (MPa)	f_{H0} (MPa)	f_{H90} (MPa)	W (N·m)
\bar{x}	15632	146	137	19,8
Cv	0.09	0.14	0.15	0.35
Min	12863	101	98	10.10
Max	18093	165	160	30.10

Considering the experimental results, the characteristic compressive strength parallel to the grain ($f_{c0,k}$) was equal to 72 MPa [8], which fits the *Dinizia excelsa* Ducke wood in the C60 strength class.

The average compressive strength parallel to the grain ($f_{c,0k}$) was 78 MPa, close to the result obtained by Grobério and Lahr (77.5 MPa) [12] with the same wood specie and higher when compared with *Mimosa tenuiflora* (58.25 MPa) [13], *Mimosa schomburgkii* (64.7 MPa) [4], *Toona ciliata* (27 MPa) [14], *Eucalyptus camaldulensis* (25.3 MPa) [15] e *Eucalyptus benthamii* (37.34 MPa) [16].

The average apparent density (ρ_{12}) was 1.13 g/cm³, considered by Grobério and Lahr a very heavy wood [12]. This value (1.13 g/cm³) was close to the *Mimosa tenuiflora* (1.06 g/cm³) [13] and higher than *Minquartia guianensis*, *Manilkara huber*, *Lecythis poiteaui* e *Mezilaurus itauba*, whose density vary between 0.867 and 0.907 g/cm³ [17]. Comparing with *Eucalyptus grandis* and *Eucalyptus cloeziana* [18], whose density range between 0.59 and 0.67 g/cm³, *Dinizia excelsa* Ducke presents a heavy wood.

Brazilian Standard ABNT NBR 7190 [8] defines the maximum value for the coefficient of variation (Cv) for the characterization to be considered as adequate, being 18% for strength in normal stresses and 28% for tangential efforts. All properties met the values of the coefficients of variation required by the standard, but the tensile strength parallel to the grain (f_{t0}), shear strength parallel to the grain (f_{v0}) and toughness (W) which exceed the limit, showing a Cv equal to 0.33, 0.23 and 0.35, respectively.

According Grobério and Lahr [11], there is the possibility the use of *Dinizia excelsa* Ducke in civil construction, including heavy duty use, structural purpose and furniture use.


Table 4. Regression models for the strength values estimation of the *Dinizia excelsa* Ducke by the apparent density

	Model	P-value	a	B	R ² (%)
f_{c0}	Lin.	0.2772	57.0412	18.1213	11.67
f_{t0}	Lin	0.3301	-4.3164	96.5804	9.48
f_{h90}	Lin	0.7993	6.004	-1.0279	0.68
f_{v0}	Geo	0.0231	15.1767	1.5241	41.78
f_{s0}	Log	0.6591	0.8901	0.1541	2.02
f_m	Exp	0.9488	105.9636	0.0266	0.04
f_{H0}	Log	0.0085	128.8897	142.7716	51.57
f_{H90}	Geo	0.0177	120.0967	1.0229	44.53
W	Geo	0.1956	1.5658	1.4814	15.97

Table 5. Regression models for the stiffness values estimation of the *Dinizia excelsa* Ducke by the apparent density

	Model	P-value	a	b	R ² (%)
E_{c0}	Exp	0.6750	21848.8375	-0.2535	1.83
E_{t0}	Log	0.8398	16798.6334	1905.0596	0.43
E_m	Exp	0.7447	14095.8894	0.0881	1.11

The models which presents p-value below 0.05 are considered significant. Good quality in the adjustment is represented when the coefficient of determination (R^2) is over 34%, being significant for R^2 values between 60% and 70% and higher [19]. The estimated properties with good quality in the adjustment were: f_{v0} , f_{h90} , f_{H0} . However, any property was considered significant (R^2 close or higher than 60%), with the hardness parallel to the fibers (f_{H0}) presenting the major value (51.57%). Figure 2 illustrate the adjustment for f_{H0} .

**Figure 2.** Best fit obtained to estimate the strength values of wood by apparent density - logarithmic

The value of determination coefficient near 80% for the toughness adjustment obtained by Almeida et. al. [10] was significantly different from the determination coefficient (15.97%) obtained for *Dinizia excelsa* Ducke wood specie. Such divergence can be justified due to use of more wood specimens and variable density, which favors the best quality in the adjustment.

In the study developed by Dias and Lahr [7], the relation of apparent density with tensile strength normal to the grain and splitting strength obtained coefficient of determination (R^2) with low values, just as for *Dinizia excelsa* Ducke. It evidences a low correlation between apparent density and this properties.

4. Conclusions

The results of this study permit us to conclude:

- According the limit values for the variation coefficient established by the Brazilian Standard, the results obtained for the characterization are valid;
- Following the Brazilian Standard parameters, this wood is classified as C60 wood due to its characteristic compression strength parallel to the grain of 72 MPa, indicating the potential use of this wood specie in civil construction heavy duty use, structural demand and furniture use;
- The regression models of apparent density as an estimator of strength and stiffness properties were significant for only three (f_{v0} , f_{H0} and f_{H90}) of 14 analyzed properties, displaying a good quality in the adjustment in these three properties but not being significant.

REFERENCES

- [1] Vidal, J. M.; Evangelista, W. V.; Silva, J. C.; Jankowsky, I. P. Preservação de madeiras no Brasil: Histórico, cenário atual e tendências, Ciência Florestal, Santa Maria – RS, v. 25, n. 1, p. 257-271, jan./mar. 2015.
- [2] Freitas, T. P.; Feuchard, L. D.; Oliveira, J. T. S.; Paes J. B.; Arantes, M. D. C. Caracterizações anatômicas e físico-mecânica da madeira *Liquidambar sp.*, Floresta, Curitiba - PR, v. 45, n.4, p. 723 - 734, dez. 2014.
- [3] Carvalho, J.O.P.; Santos, J. J.; Saldanha, E.B.; Melo, A.S.G; Nascimento, S. M; Hirai, E. H.; Castro, T. C; Coelho, A. A; Batista, R. W. C. Identificação botânica de espécies arbóreas pouco conhecidas como contribuição ao planejamento do manejo de florestas naturais no estado do Pará. In: Anais da I Conferência do Subprograma de Ciência e Tecnologia; 2008; Belém. Brasília: CNPq; 2009. p. 579.
- [4] Costa, L. J.; Lopes, C. B. S.; Reis, M. F. C.; Candido, W. L.; Faria, B. F. H.; Paula, M. O. Caracterização anatômica e descrição físico-química e mecânica da madeira de *Mimosa schomburgkii*. Floresta, Curitiba – PR, v. 47, n. 4, p. 383-390, out./dez., 2017.
- [5] Iwakiri, S.; Trianoski, R.; Fonte, A. P. N.; França, M. C.; Lau, P. C.; Molleken, R. Potencial de uso de madeiras de *Dinizia excelsa* Ducke e *Protium puncticulatum* J.F.Macbr para produção de painéis EGP. Scientia Forestalis, Piracicaba-SP, v. 44, n. 111, p. 709-717, set. 2016.
- [6] Lahr, F. A. R.; Propriedades físicas de resistência e de elasticidade de espécies de madeira para emprego em estruturas, Encontro Brasileiro de Madeiras e em Estruturas de Madeiras, v. 3, São Carlos, SP, Brasil, 1989.
- [7] Dias, F. M.; Lahr, F. A. R. Estimativa de propriedades de resistência e rigidez da madeira através da densidade aparente, Scientia Forestalis, Piracicaba - SP, n. 65, p. 102 - 113, jun. 2004.
- [8] Associação Brasileira De Normas Técnicas – ABNT. NBR 7190. Projeto de estruturas de madeira. Rio de Janeiro, 107 p., 1997.
- [9] Lobão, M. S.; Lúcia, R. M. D.; Moreira, M. S. S.; Gomes, A. Caracterização das propriedades físico-mecânicas da madeira de Eucalipto com diferentes densidades. Revista Árvore, Viçosa-MG, v.28, n.6, p. 889-894, 2004.
- [10] Almeida, D. H.; Scaliante, R. M.; Christoforo, A. L.; Varanda, L. D.; Lahr, F. A. R.; Dias, A. A.; Junior, C. C. Tenacidade da madeira como função da densidade aparente, Revista Árvore, Viçosa-MG, v.38, n.1, p.203-207, 2014.
- [11] Mesquita, M. R.; Ferraz, I. D. K.; Camargo, J. L. C. Angelim vermelho, *Dinizia excelsa* Ducke. In: Manual de Sementes da Amazônia. Fascículo, v. 8, 12p. INPA, Manaus-AM, Brasil, 2009.
- [12] Grobério, M. P.; Lahr, F. A. R. Indicações para o emprego da madeira de espécies tropicais do Brasil, Madeira: arquitetura e engenharia, n. 8, 2002.
- [13] Rocha, H. L. S.; Paes, J. B.; Miná, A. J. S.; Oliveira, E. Caracterização físico mecânica da madeira de jurema – preta (*Mimosa tenuiflora*) visando seu emprego na indústria moveleira. Agrária, Recife – PE, v.10, n. 2, p. 262-267, 2015.
- [14] Braz, R. L.; Oliveira, J. T. S.; Rodrigues, B. P.; Arantes, M. D. C. Propriedades físicas e mecânicas da madeira de *Tppnia ciliata* em diferentes idades. Floresta, Curitiba – PR, v. 43, n. 4, p. 663-670, out./dez. 2013.
- [15] Torres, P. M. A.; Paes, J. B.; Nascimento, J. W. B.; Brito, F. M. S. Caracterização físico-mecânica da madeira jovem de *Eucalyptus camaldulensis* para aplicação na arquitetura rural. Floresta e Ambiente, Seropédica – RJ, v. 23, n.1, p. 109-117, 2016.
- [16] Muller, B. V.; Rocha, M. P.; Cunha, A. B.; Klitzke, R. J.; Nicoletti, M. F. Avaliação das Principais Propriedades Físicas e Mecânicas da Madeira de *Eucalyptus benthamii* Maiden et Cambage, Floresta e Ambiente, v. 21, ed. 4, p. 535-542, 2014.
- [17] Silveira, L. H. C.; Rezende, A. V.; Vale, A. T. Teor de umidade e densidade básica da madeira de nove espécies comerciais amazônicas, Acta Amazônica, v. 43, ed. 2, p. 179-184, 2013.
- [18] Gonçalez, J. C.; Breda, L. C.; Barros, J. F. M.; Macedo, D. G.; Janin, G.; Costa, A. F.; Vale, A. T. Características tecnológicas das madeiras de *Eucalyptus grandis* W. Hill ex Maiden e *Eucalyptus cloeziana* F. Muell visando ao seu aproveitamento na indústria moveleira. Ciência Florestal, Santa Maria – RS, v. 16, n. 3, p. 329-341, 2006.
- [19] MONTGOMERY, D. C. Design and analysis in experiments. Arizona: John Wiley & Sons, 730p, 2012.